

REV LTR	DESCRIPTION	DATE	APPVD.
-	Orig.	1/10/24	MLG

**XSIS XD673S SERIES**  
**LVDS OSCILLATORS**  
**FOR SPACE & HI-REL APPLICATIONS**  
**75 MHz to 200 MHz**

( 5 x 7 mm, Straight Leads, Thru-Hole, 2.5V & 3.3V )

( Refer to Page 5 for Reduced QCI Models XD673E, XD673B & XD673P )

REV STATUS OF SHEETS	REV																
	SHEET NO.	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16
<b>APPROVALS</b>	<b>DATE</b>	<b>XSIS ELECTRONICS, INC.</b>															
PREP. N. Gupta	1/10/24	12620 W. 63 <sup>rd</sup> Street, Shawnee, KS 66216 USA															
ENG. M. Gupta	1/10/24	<b>XD673S SERIES LVDS OSCILLATORS</b>															
Q. A. S. Gupta	1/10/24																
CUST. ENG.		FSC NO. 57051								DWG. NO. XD673S							
CUST Q A.		SCALE N/A								SHEET 1 OF 9							

1. SCOPE:

XD673S, LVDS series, high reliability hybrid microcircuit crystal oscillators are designed, produced and tested by Xsis Electronics, Inc. as MIL-PRF-55310, Class "S" equivalent devices for use in advanced industrial, military, avionics and space applications. These devices are of hybrid microcircuit technology conforming to MIL-PRF-55310, Type 1, Class 2 oscillators.

1.1 ALTERNATE MODELS: Models XD673E, XD673B and XD673P with reduced QCI and/or reduced screening and shorter lead times are also offered as explained on page 5.

2. APPLICABLE DOCUMENTS:

MIL-PRF-55310F Oscillator, Crystal Controlled, General Specifications for  
MIL-PRF-38534K Hybrid Microcircuits, General Specifications for  
MIL-STD-883L Test Methods and Procedures for Microelectronics

3. REQUIREMENTS:

3.1 General: The individual item requirements shall be as specified herein.

3.2 Package: Ceramic, 90% Min. Al<sub>2</sub>O<sub>3</sub>, Weight 0.6 g Max., Thermal Resistance,  $\theta_{JC}$ : 28°C / Watt.

3.2.1 Lead Material & finish: Kovar, 50 to 85 micro-inches gold over 100 to 250 micro-inches nickel. Hot Solder tinning with Sn63/Pb37 solder per MIL-PRF-55310 is optional at an additional cost.

3.2.3 Reflow Soldering: Reflow soldering at 260°C for 10 seconds shall not degrade the performance.

3.3 Hermeticity: Resistance welded, hermetically sealed, leak rate of  $1 \times (10)^{-8}$  atm-cc/s Max.

3.4 Marking: As a minimum, the parts shall be marked with Xsis P/N, ESD symbol, date code and serial number.

3.5 Absolute Maximum Ratings: Unless otherwise specified, absolute maximum ratings shall be as follows:

Supply Voltage	-0.5 to +4.5 VDC
Operating Free-Air Temperature Range	-55°C to +125°C
Storage Temperature	-55°C to +125°C

3.6 Electrical Characteristics: See Table I

3.6.1 Total Dose Radiation: Hybrid Microcircuit Crystal Oscillators shall be capable of meeting the electrical characteristics of Para. 3.6 after being exposed to total ionizing dose radiation of 100 krad as per MIL-STD-883, method 1019.

3.7 Hybrid Elements:

3.7.1 Quartz Crystals: High grade cultured quartz crystal shall be used. As an option, Xsis will use premium Q swept quartz crystal at an additional charge, refer to part numbering example in paragraph 6 to specify swept quartz crystal. Crystal element evaluation shall be in accordance with MIL-PRF-55310.

3.7.2 Crystal Mounting: Crystal element shall be mounted at 4 points in such a manner as to provide adequate ruggedness and performance under extreme environments specified herein.

3.7.3 Passive Elements: Established Reliability (ER) QPL components, failure level R minimum shall be used or element lot evaluation shall be as per MIL-PRF-55310, class S, or MIL-PRF-38534, Appendix C, Class K as applicable.

**XSIS ELECTRONICS, INC.**

**12620 W. 63<sup>rd</sup> St., Shawnee, KS 66216 USA**

Tel: 913-631-0448 e-mail: xsis@xis.com website: www.xsis.com

**FSC NO.**

**57051**

**DWG. NO.**

**XD673S**

**REV**

**SCALE**

**N/A**

**SHEET**

**2 OF 9**

- 3.7.4 The microcircuit die shall be from lots that have passed the element evaluation per MIL-PRF-38534, Level K. In addition, ionizing radiation testing shall be performed at the oscillator level as explained in paragraph 3.7.5 herein.
- 3.7.5 The Microcircuit die shall be from wafer lots that have been successfully tested in the oscillator for ionizing radiation up to 100 krads. Xsis Electronics has also performed SET & SEL on the microcircuit die. The die is SEL immune for LET of up to 95 Mev-cm<sup>2</sup>/mg. Test reports are available on request.
- 3.7.6 Workmanship: Rework and Process controls shall be in accordance with the requirements of MIL-PRF-55310 & MIL-PRF-38534 as applicable.
- 3.7.7 Lot Traceability: Production lot for these oscillators shall be homogenous. Each element used in the production lot shall be traceable to a single lot. Swept quartz shall be traceable to the quartz bar, and its applicable processing details.
- 3.7.8 Prohibited Materials: The following items shall not be used in these oscillators: Pure Tin (Sn >97%), Cadmium, Zinc, Mercury, Selenium, Silver as under plate. Gold Plating without a nickel barrier.
- 3.7.9 Element Derating: All active and passive elements shall be derated in accordance with the applicable hybrid microcircuit requirements of MIL-STD-975. Elements shall not operate in excess of derated values.
- 3.7.10 Material Outgassing: All materials shall meet a TML of 1% Max. and a CVM of 0.1% Max., when tested in accordance with ASTM E595.
4. QUALITY ASSURANCE PROVISIONS: The quality assurance provisions shall be as specified herein.
- 4.1 100% Screening: The 100% screening shall be performed as per Table II. In addition, MIL-PRF-38534 Group B Option 1 in-line inspection for bond strength and die shear shall be performed at pre-seal inspection. PDA requirements for nondestructive bond pull and burn-in shall be as specified below.
- 4.2 PDA for Nondestruct Bond Pull: Unless otherwise specified, PDA shall be 2% of total number of wires or 1 wire whichever is greater.
- 4.3 PDA for Burn-in: Unless otherwise specified, PDA for burn-in shall be 2% or 1 oscillator whichever is greater and shall be applicable to +23°C to +25°C static tests only. In addition Delta Calculation shall be performed after Burn-in and shall count for PDA. All measured values for Delta Calculation shall be recorded. Parts that exceed the specified delta limits shall be rejected and be counted for PDA. Delta Calculation shall be performed at 2.5 VDC or 3.3 VDC, as applicable, for the following parameters:
- |                   |                    |
|-------------------|--------------------|
| Input Current     | 10% change Maximum |
| Output High Level | 10% change Maximum |
| Output Low Level  | 10% change Maximum |
- 4.4 Group A inspection shall be in accordance with MIL-PRF-55310 for product level S.
- 4.5 Group B inspection (30 day aging) shall be in accordance with MIL-PRF-55310 for product level S. In order to expedite delivery, by customer request, the aging test can be ended after 15 days if the amount of frequency aging is less than 50% of the 30 day specification limit.
- 4.6 Oscillators shall be capable of meeting group C inspection per MIL-PRF-55310. Generic group C inspection data on similar parts may be used to satisfy this requirement. When specified by the Customer, Xsis Electronics will perform Group C testing at an additional charge.

<b>XSIS ELECTRONICS, INC.</b> 12620 W. 63 <sup>rd</sup> St., Shawnee, KS 66216 USA Tel: 913-631-0448 e-mail: xsis@xis.com website: www.xsis.com	<b>FSC NO.</b> 57051	<b>DWG. NO.</b> XD673S	<b>REV</b>
	<b>SCALE</b> N/A	<b>SHEET</b> 3 OF 9	

4.7 Inspection and Test Data: Unless otherwise specified in the purchase order, the following Inspection and test data documentation shall be supplied with the parts.

( See Page 5 for the description of the Model Numbers other than XD673S )

**Model XD673S:**

Certificate of Conformance  
Summary of Screening Test Results per Table II  
PDA Calculations for Non-Destruct Bond Pull and Burn-in  
Summary of Elements Lot Traceability  
Electrical Tests before and after Burn-in  
Group A Inspection Summary  
Group B (30 day Aging) Data  
Radiographic Inspection Certificate

**Model XD673E:**

Certificate of Conformance  
Summary of Screening Test Results per Table III  
Summary of Elements Lot Traceability  
Group A Inspection Summary  
Radiographic Inspection Certificate.

**Model XD673B:**

Certificate of Conformance  
Summary of Screening Test Results per Table III  
Group A Inspection Summary  
Radiographic Inspection Certificate, if required by the Purchase Order, at additional cost

**Model XD673P:**

Certificate of Conformance

4.8 The following test and inspection options are available at customer request, at additional cost.


Customer Source Inspection for Pre-Cap and Final  
Group C Inspection per MIL-PRF-55310 on 4 or 8 units  
DPA (Destructive Physical Analysis)  
Life Test per MIL-STD-883, Method 1005, 1000 Hrs. at +125°C  
MIL-PRF-38534, Group B Inspection  
MIL-PRF-38534, Group C Inspection

5.0 PRESERVATION, PACKAGING AND PACKING:

The oscillators shall be clean, dry and packaged in a manner to provide adequate protection against electrostatic discharge, corrosion, deterioration and physical damage during shipment.

<b>XSIS ELECTRONICS, INC.</b> 12620 W. 63 <sup>rd</sup> St., Shawnee, KS 66216 USA Tel: 913-631-0448 e-mail: xsis@xis.com website: www.xsis.com	<b>FSC NO.</b> 57051	<b>DWG. NO.</b> XD673S	<b>REV</b>
	<b>SCALE</b> N/A	<b>SHEET</b> 4 OF 9	

6. PART NUMBERING EXAMPLE:



\* Overall Frequency Accuracy includes effects of Operating Temperature, Supply Voltage, Load variations and 5 year aging

**P/N Example:** XD673S- L4 -100.000 MHz = 100.000 MHz, 3.3V Oscillator, ± 50 PPM Overall Frequency Accuracy over operating temperature range of -55°C to +125°C,

**NOTE:** Besides Model XD673S above, the following additional models are available for applications that can accommodate reduced level of Elements, Screening and Quality Conformance inspection:

**XD673E: Model XD673E** uses the same design & elements as **Model XD673S** except as follows:

- 100% screening is as per Table III herein
- PDA for Burn-in is 10% or 1 unit whichever is greater
- Delta measurements of paragraph 4.3 are not applicable
- Group A inspection is as per MIL-PRF-55310, Class B
- Group B inspection (30 day aging ) per MIL-PRF-55310 is not applicable

**XD673B: Model XD673B** is same as **Model XD673E** except as follows:


- Active and Passive Elements are as per MIL-PRF-55310, Class B. Microcircuit die is similar to the one used in Model XE8S but is not from radiation tested wafer lot.
- Radiographic Inspection is not applicable, unless required by the Purchase Order at additional cost.

**XD673P: Model XD673P** is a form, fit and function equivalent prototype of **Model XD673S**.

- Prototypes may use commercial grade elements and are not screened.
- Quality Conformance inspection is not applicable.

<b>XSIS ELECTRONICS, INC.</b> 12620 W. 63 <sup>rd</sup> St., Shawnee, KS 66216 USA Tel: 913-631-0448 e-mail: xsis@xis.com website: www.xsis.com	FSC NO. <b>57051</b>	DWG. NO. <b>XD673S</b>	REV
	SCALE N/A	SHEET 5 OF 9	

7. PACKAGE OUTLINE:



Dimensions: Inches (mm)

Figure 1 - Package Configuration & Pin Connections

**Table I – Electrical Characteristics for 2.5 V & 3.3V**

Parameter	Spec. Limits
Frequency Range	75 MHz to 200 MHz
Overall Frequency Accuracy <sup>1/</sup>	See Options in Paragraph 6.0
Operating Temperature Range	See Options in Paragraph 6.0
Supply Voltage	See Options in Paragraph 6.0
Input Current (No Load)	65 mA Max.
Output Waveform	Square Wave
Output Duty Cycle	55/45% Max
Output Load	100 ohm across outputs
High Output Level	1.45V typical, 1.60 V Max.
Low Output Level	1.10V typical, 0.90 V Min.
Differential Output Voltage (Peak to Peak)	340 mV typical, 247 mV Min., 454 mV Max.
Offset Voltage	1.25 V typical, 1.125 V Min., 1.375 V Max.
Offset Error	50 mV Max.
Rise & Fall Times (20% to 80% Levels )	600 pS Max. over -55°C to +105°C 700 pS Max. over +105°C to +125°C
Tristate Input	> 0.7 Vdd or Open: Normal Output < 0.3 Vdd: High Impedance
Start-up Time	10 mS Max.
Phase Jitter	0.3 pS rms typ, (10 KHz to 20 MHz Integrated )
Frequency Aging @ 70°C	
≤ 150 MHz	± 1.5 PPM Max./30 days ± 5 PPM Max. first year, ± 2 PPM Max/year thereafter
> 150 MHz	± 2.0 PPM Max./30 days ± 6 PPM Max. first year, ± 2.5 PPM Max/year thereafter

<sup>1/</sup> Frequency Accuracy with reference to nominal frequency includes initial accuracy at 25°C, ± 5% Supply Voltage and ± 10% load variations and 5 year aging.

*Contact Xsis Engineering for any other special requirements.*

<b>XSIS ELECTRONICS, INC.</b> 12620 W. 63 <sup>rd</sup> St., Shawnee, KS 66216 USA Tel: 913-631-0448 e-mail: xsis@xis.com website: www.xsis.com	<b>FSC NO.</b> 57051	<b>DWG. NO.</b> XD673S	<b>REV</b>
	<b>SCALE</b> N/A	<b>SHEET</b> 7 OF 9	

**Table II - Model XD673S Screening (100%)**

Test - Inspection	Test Method – Condition
Nondestructive Bond Pull	MIL-STD-883, Method 2023
Internal Visual	MIL-STD-883, Method 2017, Level S
Stabilization Bake ( Prior to Seal ) <u>1/</u>	MIL-STD-883, Method 1008, Condition C ( +150°C ) 48 hours minimum
Random Vibration	MIL-STD-883, Method 2026, Condition I- B
Thermal Shock	MIL-STD-883, Method 1011, Condition A
Temperature Cycling	MIL-STD-883, Method 1010, Condition C
Constant Acceleration	MIL-STD-883, Method 2001, Condition A Y <sub>1</sub> axis only ( 5000 G )
Seal ( Fine and Gross Leak ) <u>2/</u>	MIL-PRF-55310, Para. 4.8.2.2.3
Particle Impact Noise Detection ( PIND )	MIL-STD-883, Method 2020, Condition A
Radiographic Inspection	MIL-STD-883, Method 2012, Class S
Pre Burn-in Electrical Tests: Record as applicable	Refer to Table II-a below
Burn-in	+125°C, Nominal Supply Voltage and Burn-in load 320 Hours Minimum
Post Burn-in Electrical Tests: Record as applicable	Refer to Table II-a below
External Visual	MIL-STD-883, Method 2009

1/ Vacuum bake and maintain oscillators in dry nitrogen per MIL-PRF-55310.

2/ Fine & Gross leak test is also performed per MIL-PRF-55310, Para. 4.8.2.2 after lead forming operations.

**Table II-a – Pre & Post Burn-in Electrical Tests**

Test Parameter	MIL-PRF-55310 Method	Pre BI 24 ± 1°C	Post BI 24 ± 1°C	Post BI Low Temp	Post BI High Temp
Input Current	4.8.5	✓	✓	✓	✓
Output Frequency	4.8.6	✓	✓	✓	✓
Frequency Vs. Temperature Stability	4.8.10.1	✓	✓	✓	✓
Frequency Vs. Supply Voltage	4.8.14	✓	✓	✓	✓
Output Voltage Levels	4.8.21.3	✓	✓	✓	✓
Output Rise & Fall Times	4.8.22	✓	✓	✓	✓
Output Duty Cycle	4.8.23	✓	✓	✓	✓
Start-up time	4.8.29	✓	✓	✓	✓
Tristate, if applicable	4.8.28	✓	✓	✓	✓

<b>XSIS ELECTRONICS, INC.</b> 12620 W. 63 <sup>rd</sup> St., Shawnee, KS 66216 USA Tel: 913-631-0448 e-mail: xsis@xis.com website: www.xsis.com	<b>FSC NO.</b> 57051	<b>DWG. NO.</b> XD673S	<b>REV</b>
	<b>SCALE</b> N/A	<b>SHEET</b> 8 OF 9	



**Table III - Models XD673E & XD673B, Screening (100%)**

Test - Inspection	Test Method – Condition
Nondestructive Bond Pull	MIL-STD-883, Method 2023
Internal Visual	MIL-STD-883, Method 2017, Level B
Stabilization Bake ( Prior to Seal ) <u>1/</u>	MIL-STD-883, Method 1008, Condition C ( +150°C ) 24 hours minimum
Temperature Cycling	MIL-STD-883, Method 1010, Condition B
Constant Acceleration	MIL-STD-883, Method 2001, Condition A Y <sub>1</sub> axis only ( 5000 G )
Seal ( Fine and Gross Leak )	MIL-PRF-55310, Para. 4.8.2.2.2
Particle Impact Noise Detection ( PIND )	MIL-STD-883, Method 2020, Condition A
Radiographic Inspection ( <b>Model XD673E Only</b> ) <u>2/</u>	MIL-STD-883, Method 2012, Class S
Pre Burn-in Electrical Tests: Verify all measurements	Refer to Table III-a below
Burn-in	+125°C, Nominal Supply Voltage and Burn-in load 160 Hours Minimum
Post Burn-in Electrical Tests: Verify all measurements	Refer to Table III-a below
External Visual	MIL-STD-883, Method 2009

1/ Vacuum bake and maintain oscillators in dry nitrogen per MIL-PRF-55310

2/ Radiographic Inspection is applicable to Model XD673E only

**Table III-a – Pre & Post Burn-in Electrical Tests**

Test Parameter	MIL-PRF-55310 Method	Pre BI 24 ± 1°C	Post BI 24 ± 1°C	Post BI Low Temp	Post BI High Temp
Input Current	4.8.5	✓	✓	✓	✓
Output Frequency	4.8.6	✓	✓	✓	✓
Frequency Vs. Temperature Stability	4.8.10.1	✓	✓	✓	✓
Frequency Vs. Supply Voltage	4.8.14	✓	✓	✓	✓
Output Voltage Levels	4.8.21.3	✓	✓	✓	✓
Output Rise & Fall Times	4.8.22	✓	✓	✓	✓
Output Duty Cycle	4.8.23	✓	✓	✓	✓
Start-up time	4.8.29	✓	✓	✓	✓
Tristate, if applicable	4.8.28	✓	✓	✓	✓

<b>XSYS ELECTRONICS, INC.</b> 12620 W. 63 <sup>rd</sup> St., Shawnee, KS 66216 USA Tel: 913-631-0448 e-mail: xsis@xis.com website: www.xsis.com	<b>FSC NO.</b> 57051	<b>DWG. NO.</b> XD673S	<b>REV</b>
	<b>SCALE</b> N/A	<b>SHEET</b> 9 OF 9	